



UN38.3 TEST REPORT

报告编号 : WTX22D08159608B001

Reference No.....

申请商

: CROSSCALL Applicant.....

Address : 245 RUE PAUL LANGEVIN 13290 AIX-EN-PROVENCE- FRANCE

宁波博禄德国际贸易有限公司

Manufacturer : Ningbo Broad International Trading Co., Ltd.

制造商地址

宁波市象山工业区蓬莱路 312 号

Address: No.312 Penglai Road, Xiangshan Industrial Zone, Ningbo China

产品名称 Name of product.....: Power Bank

移动电源

产品型号

Model

: X-POWER

总共页数

Total pages : 16 pages

联合国《试验和标准手册》第七修订版第38.3节

(ST/SG/AC.10/11/Rev.7 Section 38.3)

依据标准 Standards.....

Section 38.3 of the Seventh revised edition of UNITED NATIONS

Recommendations-Manual of Test and Criteria

(ST/SG/AC.10/11/Rev.7 Section 38.3)

发布日期

: 2022-10-12

Date of Issue.....

所提供的样品符合以上测试标准

Test Result: The submitted samples comply with the above standards

备注:报告未经本司的书面批准不得部分复制,检验检测结果仅对测试样品负责。报告经涂改、 增删、无批准人签字或未加盖本司检验检测专用章无效。报告未加盖资质认定标志章,则仅用于 科研、教学、内部质量控制等活动,不可用作为向社会出具具有证明作用数据的用途。

Remarks: The results shown in this test report refer only to the sample(s) tested; this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid wit hout specific stamp of test institute and the signatures of compiler and approver. If the report is not stampe d with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.

Prepared By:

Waltek Testing Group Co., Ltd.

Address: No. 77, Houjie Section, Guantai Road, Houjie Town, Dongguan City, Guangdong, China Tel:+86-769-2267 6998

Fax:+86-769-2267 6828

编辑 Complied by:

批准 Approved by:

甄锦炎 Jason Zhen /工程师 Project

Engineer

秦林伟 Deval Qin /授权签字人 Designated

Reviewer



Reference No.: WTX22D08159608B001 Page 2 of 16

产品分类 Classification:	移动电源
,m力失 Glassification	Power Bank
型号 Model::	X-POWER
额定值 Ratings:	3.7V, 6000mAh, 22.2Wh
商标 Trade mark:	N/A
标准充电电流 Standard charge current:	2.1A
最大充电电压 Max. charge voltage::	SV II WILL WILL WILL THE
最大充电电流 Max. charge current:	2.1A- (1)- (1)- (1)- (1)- (1)- (1)- (1)- (1)
标准放电电流 Standard discharge current:	2.4A
最大放电电流 Max. discharge current:	2.4A
放电截止电压 Discharge cut-off voltage:	3V 10 10 10 10 10 10 10 10 10 10 10 10 10
尺寸 Dimension:	109.6mm×70.1mm×23.2mm
报告中可能用到的结论标识 Possible test case ve	rdicts: The mark white white white
测试项目不适用该产品	THUM
test case does not apply to the test object	· · · · · · · · · · · · · · · · · · ·
测试项目符合标准的要求	A 1/4 D(656)
test object does meet the requirement	合格 P(ass)
测试项目不符合标准的要求	不合校 E(ail)
test object does not meet the requirement	不合格 F(ail)
测试 Testing:	TEK LIEK NLIEK MLIEK UNLIE UN
样品接收日期 Date of receipt of test item	: 2022-08-09
测试日期 Date(s) of performance of test	: 2022-08-09~2022-08-19
测试结论 Test conclusion:	" at the fifth that the

由 CROSSCALL 送检的移动电源,根据联合国《试验和标准手册》第七修订版第 38.3 节进行测试,测试项目见下页表格,测试结果符合标准相关要求

The Power Bank submitted by CROSSCALL are tested according to Section 38.3 of the Seventh revised edition of UNITED NATIONS Recommendations-Manual of Test and Criteria (ST/SG/AC.10/11/Rev.7 Section 38.3). Test items see table of next page. The test results comply with the relevant requirement of the standard.



样品状态 Samples' State

After 25 cycle at 50% of the design rated capacity

After 25 cycles ending in fully charged states

After 25 cycles ending in fully discharged states

第1个充放电周期,完全充电状态

At first cycle, in fully charged states

第25个充放电周期,完全充电状态

第1个充放电周期,完全充电状态

At first cycle, in fully charged states

第25个充放电周期,完全充电状态

At first cycle in fully discharged states

第1个充放电周期完全放电状态

第25个充放电周期完全放电状态

Reference No.: WTX22D08159608B001 Page 3 of 16

样品编号

Sample No.

B01#~B04#

B05#~B08#

C01#-C05#


C06#-C10#

B09#~B12#

B13#~B16#

C11#-C20#

C21#-C30#



备注:

本报告中以点号代替小数点

测试环境条件,环境温度 20℃-25℃,环境湿度: 45%-75%

分包测试: 不适用

测试项目 Test item

T1~T5

T6

T7

T8

Remarks:

Throughout this report, point is used as the decimal separator

Test environment condition, ambient temperature 20 °C-25 °C, ambient humidity 45%-75%

Subcontracted test condition: N/A



Reference No.: WTX22D08159608B001 Page 4 of 16

条款	测试要求	16. 21. 20. 20.	结果评判	结论
无动 Clause	Requirement-Test		名表 に対 Result-Remark	Verdict
	at the title of	TET ME WALL WIT	70	.4.
38.3.4	程序 /Procedure	at the	TEX TEX STEE	Р
LIEK WIFE	小型电池或电池组必须按顺序进 T.1 to T.5 are conducted in sec or battery.		TEX LIEX NITER OF	Р
EK NUTEK	试验 T.6 和 T.8 应使用未另外试 /Test T.6 and T.8 are conducte tested cells or batteries.		THE STEEL WITH MILE	EX PL
WALTER ON	试验 7 使用原先在试验 T.1 至 T 进行/Test T.7 conducted using previously used in Tests T.1 to testing on cycled batteries.	undamaged batteries	Whitek whitek whiteh	N/A
质量损失 Mass loss	用以下测试步骤 Following procedure is provided	d: Whitek whitek whitek	MUTTER MUTTER MUTTER	P
Whitek wh	质量损失(%)=(M1-M2)/M 此式中 M1 是试验前的质量,M 质量损失不超过下表所列的数值 Mass loss(%)=(M1-M2)/M1*100 Where M1 is the mass before the mass after the test. When mass the values in below table, it sha mass loss"	2 是试验后的质量。如果 f,即为"无质量损失" D he test and M2 is the s loss does not exceed	et white white white	antifet
	电芯或电池质量 M Mass M of cell or battery M<1g 1g≤M≤75g M≥75g	质量损失限制 Mass loss limit 0.5% 0.2% 0.1%	THE WHITE WALTER WAS	Vile M Vile M
38.3.4.1		: Altitude Simulation	L St St St	Р
38.3.4.1.1		A A A A A A A A A A A A A A A A A A A	The state of the s	P
30.3.4.1.1	目的/Purpose 本试验模拟在低压条件下的空运	7This test simulates air	A OF OF	10
	transport under low-pressure co		WITE WILL WALL	Mr
38.3.4.1.2	试验程序/Test procedure	any any an	The state of the s	PΡ
The Mark	存储气压/Stored at a pressure	CER TER TER	11.6 kPa	-tn
* 15*	环境温度/Ambient temperature	(20 ± 5°C)	23.4℃	* X
Mrs	存储时间/Stored times(≥ 6 ho	urs)	6 hours	711
38.3.4.1.3	要求/Requirement	very any any		P
WALTER WALTER	无渗漏、无排气、无解体、无破验电芯或电池在试验后的开路电验前电压的 90%,电压的要求不验电池和电池组 / No leakage, r disassembly, no rupture and no voltage of each test cell or batter less than 90% of its voltage improcedure. The requirement relapplicable to test cells and batter applicable to test cells	也压不小于其在进行这一试适用与完全放电状态的试 no venting, no offire and the open circuit ery after testing is not mediately prior to this lating to voltage is not	无渗漏、无排气、无解体、无破裂和无起火,数据见表 1 / No leakage, no venting, no disassembly, no rupture and no fire. The data see Table 1	MITER IN



Reference No.: WTX22D08159608B001 Page 5 of 16

410	ST/SG/AC.10/11/Rev.7/ Section 38	.3 41 41 41	44
条款 Clause	测试要求 Requirement-Test	结果评判 Result-Remark	结论 Verdict
38.3.4.2	试验 T.2 温度试验/ Test T.2: Thermal Test	TEX STEX SLIEN	Р
38.3.4.2.1	目的/Purpose	My My My	Р
NITER WALTE	本试验评估电池和电池组的密封完善性和内部电连接,试验是利用迅速和极端的温度变化进行/This test assesses cell and battery seal integrity and internal electrical connections. The test is conducted using rapid and extreme temperature changes.	Mitek whitek whitek w	nite whi ex white
38.3.4.2.2	试验程序/Test procedure	- L A A	- P
mr. m	试验温度和存储时间/ Test temperature and stored hours	1) 72±2°C, ≥6h 2) -40±2°C, ≥6h	Mr.
NALTER WALTER	两个极端试验温度的最大间隔时间/The maximum time interval	极端温度之间间隔时间 ≤30min /Between test temperature extremes is ≤30 minutes.	MALTE WA TEK MALT
et let	测试时间/ Test times	重复 10 次/Repeated 10 times	# AP
JUNE 1	所有电池和电池组在环境温度(20±5℃)下存放 24 小 /After which all test cells and batteries are to be stored for 24 hours at ambient temperature (20±5℃).	环境温度/Ambient temperature 23.2℃	ALC: TEX
WILLER WATE	对于大型电池和电池组,暴露于极端试验温度的时间至少应为 12 小时/For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours	while whitek whitek	N/A
38.3.4.2.3	要求/Requirement	4 24	P C
WALTER WALTER	无渗漏、无排气、无解体、无破裂和无起火,并且每个试验电芯或电池在试验后的开路电压不小于其在进行这一试验前电压的 90%,电压的要求不适用与完全放电状态的试验电池和电池组 / No leakage, no venting, no disassembly, no rupture and no fire and the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.	无渗漏、无排气、无解体、无破裂和无起火; 数据见表 1/ No leakage, no venting, no disassembly, no rupture and no fire. The data see Table 1	LIEK WILL



Reference No.: WTX22D08159608B001 Page 6 of 16

20,	ST/SG/AC.10/11/Rev.7/ Section 38	3, m, m, m,	40
条款 Clause	测试要求 Requirement-Test	结果评判 Result-Remark	结论 Verdict
38.3.4.3	试验 3 振动 /Test T.3: Vibration	at at set	.√P
38.3.4.3.1	目的/ Purpose	They will have	Р
Z- Z-	本试验模拟运输过程中的振动/This test simulates		16
	vibration during transport.	TER STEE STEE	10 - W
38.3.4.3.2	测试程序/ Test procedure	10, 27, 20, 20	Р
00.0.4.0.2	电池和电池组以不使电芯变形且能正确地传播振动的方	A A A A	
	式紧固在振动机平面上/Cells and batteries are firmly	The Mary Mary Mary	2/1
	secured to the platform of the vibration machine without		P
	distorting the cells in such a manner as to faithfully transmit the vibration.	A MULTER MULTER MULTE	MULT
A 1	振动应以正弦波形振动,频率在 7Hz 和 200Hz 之间摆动	a at at	45
	再回到 7Hz 的对数扫频为时 15min / The vibration shall	ALTER OLIVE WALL	Mrs. W
	be a sinusoidal waveform with a logarithmic sweep	24. 25. 2.	Р
	between 7Hz and 200Hz and back to 7Hz traversed in	LET TEX TEXT	CIET IN
7/11.	15minutes.	Fry are and	- 70,
	从 7HZ 开始保持 1 gn 的最大加速度直到频率达到 18HZ,	1 1 1 1 1	* 4
	然后将振幅保持在 0.8mm(总偏移 1.6mm)并增加频率直	ER SLIEN WITH MUI	" The
	到最大加速度达到 8 g _n (频率约为 50HZ)。将最大加速度	211. 21. 2.	
	保持在 8 g _n 直到频率增加到 200HZ /From 7 Hz to a	- At Let State	LITE
	peak acceleration of 1 g _n is maintained until 18Hz is reached. The amplitude is then maintained at 0.8mm	West Mur Mar	₩ P
	(1.6mm total excursion) and the frequency increased		- X
	until a peak acceleration of 8 g _n occurs (approximately	Clien Will a	100 11
	50 Hz). A peak acceleration of 8 g _n is then maintained	2 Jun 20, 1	
of Jan	until the frequency is increased to 200 Hz	- + 11 t	
	振动须对三个互相垂直的电池安装方位的每一方向都重	rie aut. Mr. M.	211
	复进行 12 次,总共 3 小时。其中一个方向必须与端面垂		L 25
	直/This cycle shall be repeated 12 times for a total of 3	EX LIER SLIEN WILL	Р
	hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration	211. 211. 211.	
	must be perpendicular to the terminal face.	at let let	1500
38.3.4.3.3	要求/ Requirement	were men men	Р
Jet 16	试验中和试验后无渗漏、无排气、无解体、无破裂和无	4 4 4	46th .
	起火,并且每个试验电芯或电池在第三个垂直安装方位	LITER RUTE MILL N	er ar
	上的试验后的立即测得开路电压不小于其在进行这一试	无渗漏、无排气、无解	4
	验前电压的90%,电压的要求不适用与完全放电状态的试	体、无破裂和无起火,	Er CLI
	验电池和电池组/No leakage, no venting, no	数据见表 1/ No	101
	disassembly, no rupture and no fire during the test and	leakage, no venting,	P
	after the test and the open circuit voltage of each test	no disassembly, no	When.
	cell or battery directly after testing in its third	rupture and no fire	
	perpendicular mounting position is not less than 90% of	during the test .The data see Table 1	LUE
	its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test	uata see Table T	21, 27
	cells and batteries at fully discharged states.	, J , , t	4



Reference No.: WTX22D08159608B001 Page 7 of 16

	ST/SG/AC.10/11/Rev.7/ Section 38.3	
条款	测试要求 结果评判	结论
Clause	Requirement-Test Result-Remark	ark Verdict
38.3.4.4	试验 4 冲击/ Test T.4: Shock	MITE MIP
38.3.4.4.1	目的/ Purpose	Р
THE WATE	本试验评估电池和电池组抵抗累计冲击的耐受程度/This test assesses the robustness of cells and batteries against cumulative shocks	NITE WILLE
38.3.4.4.2	测试程序 /Test procedure	P
WALTER W	试验电池和电池组用坚硬的支架固定在试验装置上,支架支撑着每个试验电池的所有安装面;/Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery.	White We
TEX MUTTER	电池经受峰值加速度 150 g _n 和脉冲持续时间 6ms 的半正 弦波冲击/Each cell shall be subjected to a half-sine shock of peak acceleration of 150 g _n and pulse duration of 6milliseconds.	TEX TEX PART
MULLER	大电池经受峰值加速度 50 g _n 和脉冲持续时间 11ms 的半 正弦波冲击/Alternatively, large cells may be subjected to a half-sine shock of peak acceleration of 50 g _n and pulse duration of 11 milliseconds.	N/A
inex unitex	每个电池需经受半正弦波冲击的峰值加速度取决于电池的质量。小型电池组的脉冲持续时间为 6ms,大型电池组为 11ms。以下提供的公式用来计算适合的最小峰值加速度/Each battery shall be subjected to a half-sine shock of peak acceleration depending on the mass of the battery. The pulse duration shall be 6 milliseconds for small batteries and 11 milliseconds for large batteries. The formulas below are provide to calculate the appropriate minimum peak accelerations.	MALIER WILLER WILLER
UNLIER WALTER	Battery Minimum peak acceleration Pulse duration 150 g _n or result of formula Small batteries $Acceleration(g_n) = \sqrt{\frac{100850}{mass^2}}$ 6ms Whichever is smaller 50 g _n or result of formula Large $Acceleration(g_n) = \sqrt{\frac{30000}{mass^2}}$ 11ms	MULTER MULTER
MILITER WHIT	Whichever is smaller 每个电池和电池组在三个互相垂直的安装方位的正方向 经受三次冲击,接着反方向经受三次冲击,总共经受 18 次冲击/Each cell or battery shall be subjected to three	MITER MITER
	shocks in the positive direction and to three shocks in the negative direction in each of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks.	TEK WY



Reference No.: WTX22D08159608B001 Page 8 of 16

	ST/SG/AC.10/11/Rev.7/ Section 38	·3 Me M. M.	
条款 Clause	测试要求 Requirement-Test	结果评判 Result-Remark	结论 Verdic
38.3.4.4.3	要求/Requirement	THE LIFE MITE	, CUP
LIEK WILLER	无渗漏、无排气、无解体、无破裂和无起火,并且每个试验电芯或电池在试验后的开路电压不小于其在进行这一试验前电压的 90%,电压的要求不适用与完全放电状态的试验电池和电池组/No leakage, no venting, no disassembly, no rupture and no fire and the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.	无渗漏、无排气、无解体、无破裂和无起火,数据见表 1 /No leakage, no venting, no disassembly, no rupture and no fire. The data see Table 1	EL PLI
38.3.4.5	试验 5 外部短路 /Test T.5: External Short Circuit	Were Mary Mer.	Р
38.3.4.5.1	目的/ Purpose	LEK TEK TEK	J P
t lik	本试验模拟外部短路/This test simulates an external short circuit.	in the the	**
38.3.4.5.2	试验程序 /Test procedure	EL OLIE WALTER WALT	Р
White white	下后开始测试。时间根据电池和电池组的尺寸和设计,评估和记录加热时间。如果不可评估此值,小型电池和电池组需至少暴露 6h,大型电池和电池组需 12h//The cell or battery to be tested shall be heated for a period of time necessary to reach a homogeneous stabilized temperature 57±4°C, measured on the external case. This period of time depends on the size and design of the cell or battery and should be assessed and documented. If this assessment is not feasible, the exposure time shall be at least 6 hours for small cells and small batteries, and 12 hours for large cells and large batteries.	White	MILLER DE LE
	在 57±4℃温度下,电池和电池组需经受外部电阻 0.1ohm 的短路试验/Then the cell or battery at 57±4℃ shall be subjected to one short circuit condition with a total external resistance of less than 0.1 ohm.	while anifek anifek a	LIE P
WALTER WA	电池和电池组外部壳体温度恢复到 57±4℃后,短路需持续至少 1 小时,或大型电池组壳体温度值下降测试中最高温升值的一半,并且保持在这个值以下/This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to 57±4℃, or in the case of the large batteries, has decreased by half of the maximum temperature increase observed during the test and remains below that value.	TEX TIEX WITEX WITEX	ek whi
38.3.4.5.3	要求/ Requirement	Mr. M. M.	Р
TE WALTER	外壳温度不超过 170℃,并且在试验过程中及试验后 6 小时内无解体、无破裂、无起火 Cells and batteries external temperature does not exceed 170℃ and there is no disassembly, no rupture and no fire during the test and within six hours after this test.	试验过程中及试验后 6 小时内无解体、无破 裂、无起火,数据见 表 2 / No disassembly, no fire during the test and within six hours after this test. The data	TE VIN



Reference No.: WTX22D08159608B001 Page 9 of 16

条款	测试要求	结果评判	结论
元 永 Clause	网络女子 Requirement-Test	日本 (アナ) Result-Remark	Verdict
Olduse	Trequirement rest	result remain	VOIGIO
WITEH WY	Countil must make my the fix	see Table 2.	MILITEE.
38.3.4.6	试验 6 撞击/挤压 Test T.6: Impact / Crush	Mr. Mr. Mr.	A P
		LITTE NOTE WITH	
38.3.4.6.1	目的 /Purpose	1. 20, 20,	Р
	本试验模拟撞击或挤压等可能造成内部短路的机械性破坏/These tests simulate mechanical abuse from an	TEX WHITEK WHITEK W	i Er ynti
TEFF 15	impact or crush that may result in an internal short circuit.	t at let of	Et JEK
20 2 4 6 2	试验程序-撞击(适用于直径不小于18毫米的圆柱形电	mer in in	NI/A
38.3.4.6.2	池) /Test procedure – Impact (applicable to cylindrical cells not less than 18.0 mm in diameter)	at let let	N/A
200	将式样电池或元件电池放在平坦光滑的表面上。一根 316	and with the	40000
	型不锈钢棒横放在试样中心,钢棒直径 15.8 mm ±	at at	18
	0.1mm,长度至少 6cm,或电池最长端的尺度,取二者之	LIER SLIE WILL S	10, 10,
	长者。将一块 9.1 kg ±0.1kg 的重锤从 61 ± 2.5cm 高处	211. 20. 2	
	跌落到钢棒和试样交叉处,使用一个几乎没有摩擦的,	at at let .	JE 156
	对落体重锤阻力最小的垂直轨道或管道加以控制。垂直	the super super	21/2
	管道或管道用于引导落锤沿与水平支撑表面呈 90° 落下		4 4
	/The test sample cell or component cell is to be placed	- TEX ITER SITE	" OLLIV
	on a flat smooth surface. A 15.8 mm ± 0.1mm diameter,	Wer The Mr.	N/A
	at least 6 cm long, or the longest dimension of the cell,	11 1 1	IN/A
	whichever is greater, Type 316 stainless steel bar is to	OLIF WITH	apto al
	be placed across the centre of the sample. A 9.1 kg ±	20, 20,	
	0.1 kg mass is to be dropped from a height of 61 ± 2.5	# . III*	J. C. C.
	cm at the intersection of the bar and sample in a	The Will Will M	12 m
	controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling	70. 7	1 1
	mass. The vertical track or channel used to guide the	at left the s	The City
	falling mass shall be oriented 90 degrees from the	are we we	40
	horizontal supporting surface.	- L A	- 15+
المري المالي	接受撞击的试样,纵轴应与平坦表面平行并与横放在试	alter alter action	NU.
	样中心的直径 15.8 mm ± 0.1mm 弯曲表面的纵轴垂直;每	21/2 20, 20	
	一个试样只经受一次撞击/The test sample is to be	at the let	160
	impacted with its longitudinal axis parallel to the flat	white white white	N/A
	surface and perpendicular to the longitudinal axis of the		
	15.8 mm ± 0.1mm diameter curved surface lying across	Et JEK JEK S	The Will
	the centre of the test sample. Each sample is to be	in the the	729.
104	subjected to only a single impact.		4 24
	试验程序-挤压(适用于棱柱形、袋装、硬币/纽扣电芯和	" WITE WITE WILL	White.
38.3.4.6.3	直径小于18mm的圆柱形电池)/Test Procedure – Crush	24, 24, 25	Р
	(applicable to prismatic, pouch, coin/button cells and	IN THE TEN	100
elle.	cylindrical cells less than 18.0 mm in diameter) 将电池或元件电池放在两个平面之间挤压,挤压力度逐	and with with	40, 0
			A+
	渐加大,在第一个接触点上的速度大约 1.5cm/s。挤压持	THE THE LIER	11 July 101
	续进行,直到出现三种情况之一: /A cell or component	in the the of	Р
	cell is to be crushed between two flat surfaces. The	1 1	2 × 20
	crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to	EX LIFE OUTE JOY	- ONL
	be continued until the first of the three options below is	The The The	



Reference No.: WTX22D08159608B001 Page 10 of 16

71/2	ST/SG/AC.10/11/Rev.7/ Section 38	3 Mer Mer May	- 4
条款 Clause	测试要求 Requirement-Test	结果评判 Result-Remark	结论 Verdict
nli ^{El} anli	reached.	TEX STEE SUITER	anlifek
The The	施加的力量达到 13 kN ± 0.78kN The applied force reaches 13 kN ± 0.78 kN;	⊠ Reach this condition	P
ur au	电池的电压下降至少 100mV The voltage of the cell drops by at least 100 mV;	☐ Reach this condition	N/A
TER MULTER	电池变形达原始厚度的 50%或以上/The cell is deformed by 50% or more of its original thickness.	☐ Reach this condition	N/A
L MITEK	每个测试的电池或元件电池只做一次挤压试验/Each test cell or component cell is to be subjected to one crush only.	t lifet night mile	PER
	试验样品需观察 6 小时/The test samples shall be observed for a further 6h	711 21 34	P
Mer wer	试验应使用之前未做过其他试验的电池或元件电池进行 /The test shall be conducted using test cells or component cells that have not previously been subjected to other tests.	white white white	P
38.3.4.6.4	要求/ Requirement	in me me in	Р
Whitek was	外壳温度不超过 170 °C,并且在试验过程中及试验后 6 小时内无解体、无破裂、无起火/Cells and component cells meet this requirement if their external temperature does not exceed 170 °C and there is no disassembly and no fire during the test and within six hours after this test.	在试验过程中及试验后 6 小时内无解体、无破 裂、无起火;数据见表 3 /No disassembly and no fire during the test and within six hours after this test. The data see Table 3	MILITER WILLIAM
11 21		1 1/12 1/11 1/2	, ,,
38.3.4.7	试验 7 过度充电 /Test T.7: Overcharge	the little	CER PUTE
38.3.4.7.1	目的 /Purpose 本试验评估可充电电池承受过度充电状况的能力/This test evaluates the ability of a rechargeable battery to withstand an overcharge condition.	A STEE WILE MILE	P P
38.3.4.7.2	试验程序/Test procedure	- 1 A	Р
MUTIC AUT	充电电流是制造商建议的最大持续充电电流的两倍 The charge current shall be twice the manufacturer's recommended maximum continuous charge current.	2.1A×2=4.2A	P
EK WALTER WA	试验的最小电压如下: /The minimum voltage of the test shall be as follows: a)制造商建议的充电电压不大于 18V 时,试验的最小电压是电池组最大充电电压的两倍或 22V 两者中的较小者 /When the manufacturer's recommended charge voltage is not more than 18V,the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V.	5V×2=10V	ek whitek P
INLIER WHITE	b) 制造商建议的充电电压大于 18V 时,试验的最小电压应为最大充电电压的 1.2 倍/When the manufacturer's recommended charge voltage is not more than 18V,the minimum voltage of the test shall be 1.2 times the maximum charge voltage.	united whited whited a	N/A
-ادر ا	试验环境温度/ Ambient temperature.	22.8℃	· +
اله. الماراد	试验的进行时间/ The duration of the test.	24h	NILL.
38.3.4.7.3	要求 /Requirement	20, 20, 20,	Р



Reference No.: WTX22D08159608B001 Page 11 of 16

	ST/SG/AC.10/11/Rev.7/ Section 38	3. 4. 4.	
条款	测试要求	结果评判	结论
Clause	Requirement-Test	Result-Remark	Verdict
untrer uni trek untre ek untrek	充电电池在试验过程中和试验后 7 天内无解体,无起火/Rechargeable battery is no disassembly and no fire during the test and within seven days after the test.	试验过程中和试验后 7 天内无解体,无起火; 数据见表 4/ No disassembly and no fire during the test within seven days after the test. The data see Table 4	united v
38.3.4.8	试验 8 强制放电 / Test 8: Forced discharge	70, 2,	Р
38.3.4.8.1	目的 Purpose	t the the the	Р
unitek unit	本试验评估原电池或充电电池承受强制放电状况的能力 / This test evaluates the ability of a primary or a rechargeable cell to withstand a forced discharge condition.	Whitek whitek whilek	on liter of
38.3.4.8.2	试验程序/Test procedure	at at all	P
united a	每个电池应在环境温度下与 12V 直流电电源串联在起始电流等于制造商给定的最大放电电流的条件强制放电/ Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12 V DC, power supply at an initial current equal to the maximum discharge current specified by the manufacturer.	EX WHITEX WHITEX WHITE - TEX TEX	P.TE
EX WALLEY	将适当大小和额定值的电阻负荷与试验电池串联,计算得给定的放电电流。对每个电池进行强制放电,放电时间(小时)应等于其额定容量迟疑初始试验电流(安培)/ The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell, Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).	The white white white white white	Pertek Mi FEK Part Martik
38.3.4.8.3	要求/Requirement	700	Р
TEX MILIER	原电池或充电电池如在试验过程中和试验后 7 天内无解体,无起火/ Primary or rechargeable cells meet this requirement if there is no disassembly and no fire during the test within seven days after the test.	试验过程中和试验后 7 天内无解体,无起火。 数据见表 5 / No disassembly and no fire during the test within seven days after the test. The data see Table 5	unii v LEEK Puni EK Walfe



Reference No.: WTX22D08159608B001 Page 12 of 16

Test data:

Table	1 T.1~T.	4	7.E.F	1 Carl	J.E.	CLIE	Will.	Will.	W. C.	20, 0		٠.	J+	et :	Contraction of	Elle Li	ier inc	LE MALL	Me
	Test k	oefore	T.1	: Altitud	de Simul	ation	S	T.2: The	ermal Te	st	500	T.3 \	/ibration	in also	ale	T.4	Shock		, i
No.	Mass (g)	OCV (V)	Mass (g)	OCV (V)	Mass loss (%)	Residu al OCV (%)	Mass (g)	OCV (V)	Mass loss(%)	Residual OCV (%)	Mass (g)	OCV (V)	Mass loss (%)	Residu al OCV (%)	Mass (g)	OCV (V)	Mass loss (%)	Residua I OCV (%)	Resu t
B01#	200.4 38	5.159	200.4 34	5.158	0.002	99.98	200.3 95	5.145	0.019	99.75	200.3 93	5.144	0.001	99.98	200.3 91	5.143	0.001	99.98	Р
B02#	200.7 82	5.148	200.7 80	5.148	0.001	100.00	200.7 44	5.142	0.018	99.88	200.7 40	5.141	0.002	99.98	200.7 40	5.141	0.000	100.00	Р
B03#	199.8 79	5.162	199.8 76	5.161	0.002	99.98	199.8 43	5.147	0.017	99.73	199.8 41	5.146	0.001	99.98	199.8 41	5.145	0.000	99.98	Р
B04#	199.9 65	5.155	199.9 63	5.154	0.001	99.98	199.9 29	5.143	0.017	99.79	199.9 27	5.142	0.001	99.98	199.9 26	5.142	0.001	100.00	Р
B05#	200.6 26	5.161	200.6 24	5.160	0.001	99.98	200.5 88	5.146	0.018	99.73	200.5 86	5.145	0.001	99.98	200.5 84	5.144	0.001	99.98	√, b
B06#	200.7 44	5.149	200.7 42	5.149	0.001	100.00	200.7 08	5.141	0.017	99.84	200.7 04	5.140	0.002	99.98	200.7 04	5.140	0.000	100.00	CLI P
B07#	201.3 47	5.154	201.3 45	5.154	0.001	100.00	201.3 13	5.142	0.016	99.77	201.3 09	5.141	0.002	99.98	201.3 09	5.140	0.000	99.98	Р
B08#	201.2 85	5.156	201.2 81	5.155	0.002	99.98	201.2 45	5.141	0.018	99.73	201.2 43	5.140	0.001	99.98	201.2 40	5.140	0.001	100.00	Pol

Reference No.: WTX22D08159608B001

Table 2 T.5 External short circuit					
No.	OCV (V)	Max. Temp (°C)	Result		
B01#	5.143	57.0	Р		
B02#	5.141	56.8	LIE P		
B03#	5.145	56.8	Р		
B04#	5.142	57.1	Р		
B05#	5.144	57.2	P		
B06#	5.140	57.2	Р		
B07#	5.140	56.9	P		
B08#	5.140	57.0	Р		

Page 13 of 16

Table 3 T.6 Impact / Crush						
No.	OCV (V)	Max. Temp(°C)	Result			
C01#	3.795	23.5	Р			
C02#	3.787	23.6	Р			
C03#	3.789	23.5	P			
C04#	3.772	23.7	Р			
C05#	3.787	23.7	AL P			
C06#	3.778	23.6	IT P			
C07#	3.794	23.7	Р			
C08#	3.783	23.8	Pr.			
C09#	3.781	23.5	P			
C10#	3.769	23.6	Р			



É	J. J. E.	Table 4 T.7 Overcharge						
	No.	Max. Temp (°C)	Result	No.	Max. Temp (°C)	Result		
S	B09#	23.4	NP.	B13#	23.7	P		
	B10#	23.6	Р	B14#	23.4	WP.		
S	B11#	23.4	Р	B15#	23.6	P		
Ó	B12#	23.5	LIT'P UN	B16#	23.5	Р		

Table 5 T.8 Forced discharge									
No.	OCV (V)	Result	No.	OCV (V)	Result				
C11#	3.146	Р	C21#	3.154	P				
C12#	3.117	Р	C22#	3.168	on P				
C13#	3.128	Р	C23#	3.152	JEP.				
C14#	3.129	P. P.	C24#	3.126	Р				
C15#	3.152	P P	C25#	3.147	Р				
C16#	3.101	Р	C26#	3.152	Р				
C17#	3.125	Р	C27#	3.145	WP.				
C18#	3.144	Р	C28#	3.153	Р				
C19#	3.123	UNLIP UN	C29#	3.111	Р				
C20#	3.113	Р	C30#	3.109	JE P				

Photos

X-POWER - IP67 POWER BANK 6000 mAh LI-lon//3.7V,22.2 Wh

Photo 1



Photo 2



Photo 3






Photo 4




Photo 5









Photo 6



===== End of Report =====